

AFCONA - 2022



Chemical Composition

Silicone containing defoaming polymer.

Product general description

A strong defoamer but easy to incorporate. Silicone containing version of AFCONA-2020 which defoaming property is very strong.

Product properties

AFCONA-2022 prevents formation of foam and blisters during the manufacturing and application of solvent-based and solvent-free coatings.

AFCONA-2022 is particularly suitable defoamer that works during production and application. Especially in curtain coating processes. when foam causes a problem during packaging, AFCONA-2022 can be added slowly, while stirring to speed up the bubble breaking process.

Comparing to AFCONA-2020, AFCONA-2022 has much better de-aeration property due to the presence of silicone. However, AFCONA-2020 has better anti-foam performance.

AFCONA-2022 has better in-can transparency than AFCONA-2020.

AFCONA-2022 can be used in:

- 1) two-pack systems based on polyurethane and epoxy resins.
- 2) baking paints based on alkyd resins, acrylic and saturated polyesters.
- 3) air-drying industrial coating based on long and medium-oil alkyd resins.
- 4) protective coatings.

Product Specification

Solvent	Xylene/Butyl Acetate/ PMA/ Ethyl Acetate
Density	0.88 – 0.90g /cm ³ (20°C)
The refractive index	1.458 - 1.468(25°C)
Flash point	30°C
Appearance	Clear, colorless to slightly yellow liquid(25°C)

Addition and dosage

0.1- 1.0% on total formulation. In general under normal conditions, the dosage is 0.20 – 0.50% based on total formulation.

Incorporation

AFCONA-2022 can be incorporated prior to processing. If added subsequently, good dispersion must be ensured.

Storage

AFCONA-2022 should be stored in a cool and dry place. When kept in an original unopened container, it will keep up for 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 170kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.