

AFCONA - 5220



Chemical Composition

An acidic polyester phosphorous compound.

Product general description

Anionic wetting and dispersing additive for inorganic pigments, mainly for TiO₂ and extenders.

Product Properties:

AFCONA-5220 helps to wet and disperse inorganic pigments, mainly TiO₂, and extenders. AFCONA - 5220 is special designed as effective dispersant for TiO₂. Therefore, recommended for pure white systems.

AFCONA - 5220 has below special properties and recommended in below systems:

- 1) AFCONA - 5220 is tailor made as effective dispersant for TiO₂ and extenders.
- 2) It has very good viscosity reduction properties. In high extender loaded systems, like UPE in artificial marble, AFCONA 5220 gives very strong viscosity reduction to allow higher filler loading.
- 3) Due to the effective viscosity reduction, it also decreases dispersing time.
- 4) AFCONA-5220 is particularly suitable for the following coating systems:
 - Automotive (OEM and refinish)
 - General industrial
 - Coil coating
 - Acid curing
 - UPE
 - Epoxy
 - Polyurethane
- 5) In electrostatic spraying system for pure white paint, AFCONA - 5220 gives the highest gloss performance.

Note: AFCONA - 5220 will become slightly hazy at temperatures below 5° C. Even at - 15° C the slight haziness stay the same. This will not influence the quality.

Product Specification

Non-volatile matter	≥91% (120°C,0.5h)
Density	1,12 - 1,16g/cm ³ (20°C)
Acid Value	80 – 100 mgKOH/g
Flash point	>100°C
Gardner Color	Max.6
Appearance	Clear to slightly yellow liquid(25°C)

Addition and dosage

1.0 - 3.0% based on TiO₂ or extenders
5.0 - 10.0% based on other inorganic pigments.

Incorporation

AFCONA-5220 should be added prior to the dispersion process.

Storage

AFCONA-5220 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

30kg and 210 kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.