

AFCONA - 2721



Chemical Composition

Silicone based defoamer.

Product general description

AFCONA-2721 is a specially designed defoamer for UV-curable coatings. It can be soluble in active acrylic monomers and cross-linking with the system. Because of its good compatibility with both components of silicone and silicone-free, it has excellent defoaming and deaeration performance. Benefit of the good compatibility of AFCONA-2721, it will not cause defect like haziness.

Product properties

AFCONA-2721 is an ideal defoamer with good compatibility. It is specially designed for UV-curable coatings and plays as active solvent which can join in the reaction with the system.

AFCONA-2721 can be used in pigmented or non-pigmented resin systems such as:

- 1) UV curing system
- 2) Electron beam curing system

Product Specification

Solvent	2-ethylhexyl acrylate/ 2,6-Dimethyl-4-heptanone
Density	0.86 – 0.88 g /cm ³ (20°C)
The refractive index	1.425- 1.435(25°C)
Flash point	61°C
Appearance	Clear to slightly hazy, colorless liquid(25°C)

Addition and dosage

0.1 -1.0% on total formulation. In general under normal condition, the dosage is 0.2 – 0.5% based on total formulation.

Incorporation

AFCONA-2721 can be easily mixed, and the performance of anti-foaming will be improved by well-mixing.

Storage

AFCONA-2721 should be stored in a cool and dry place. When kept in an original unopened container, it will keep up for 2 years from the date of manufacture. The expiry date is indicated on the container.

Packaing

25kg and 170kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.