

AFCONA - 1501



Chemical Composition

Modified fatty acid polymer

Product general description

Water-based dispersing resin for the production of universal water-based pigment concentrates.

Product Properties:

AFCONA-1501 is a universal water-based dispersing resin that provides good pigment wetting and stability. It demonstrates excellent compatibility with common water-based coating components, including aqueous emulsions, water-soluble resins, and aqueous secondary dispersions.

Due to the primary hydroxyl groups, AFCONA-1501 can cross-link with both baking systems and polyurethane systems.

Complete water-solubility will be obtained by addition of e.g. 8% AMP 95.

AFCONA-1501 is recommended to be combined with other high molecular weight dispersants, such as AFCONA-4560, AFCONA-4570, or AFCONA-6225, for the preparation of water-based pigment concentrates.

AFCONA-1501 is characterized by the following:

- 1) Good compatibility and easy incorporation with low-shear mixing.
- 2) Help to provide better pigment stability.
- 3) Help to prevent drying of pigment paste on the surface and on the wall of the container.
- 4) Cross-linking capability in systems such as PU and baking paints.

Product Specification

Non-volatile matter	≥ 96% (150°C, 0.5h)
Density	1.04 - 1.06 g/cm ³ (20°C)
Acid Value	34 - 45 mg KOH/g
Gardner color	Max.5
Flash point	>100°C
Appearance	Yellow transparent liquid (25°C)

Addition and dosage

For Pigment concentrate:

Inorganic pigments: 4-5 times of solid dispersant

Organic pigment: 3-5 times of solid dispersant

Incorporation

AFCONA-1501 is recommended to add in before milling.

Storage

AFCONA-1501 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

30kg and 210 kg non-returnable containers

For product safety information: please take reference of SDS.

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.