

AFCONA - 3031



Chemical Composition

Organic modified polyether polysiloxane.

Product general description

Slip and levelling additive used mainly in metal and UV coatings.

Product Properties:

AFCONA-3031 is a polyether modified polysiloxane. It gives very good slip and the slip characteristic is oily type also called as wet look appearance. Therefore, it can enhance visually film thickness AFCONA – 3031 normally used in metal coatings like industrial baking systems, car refinish polyurethane top clear coats and other vehicle paint.

AFCONA – 3031 also widely used in UV coatings due to the good leveling and slip performance. However, it does not contain any reactive functional group that can cross-link with UV resin system.

Due to its high surface activity, AFCONA-3031 can interfere with intercoat adhesion when recoated without sanding. If air is introduced by the application equipment, the use of small amounts of defoamers such as AFCONA-2020 and AFCONA-2022 are recommended.

AFCONA – 3031 is recommended in below systems:

- 1) 2K Polyurethane. It gives low sensitivity to inner bubble.
- 2) Industrial baking systems where baking temperature is less than 170°C. In normal case, AFCONA – 3030 is recommended for industrial baking systems. However, if higher slip is needed, AFCONA -3031 will be the better choice.
- 3) UV coatings. A lot of time, AFCONA – 3031 is selected for UV due to the less foam stabilizing effect and good compatibility.

Product Specification

| | |
|----------------------|--|
| Non-volatile matter | 50 - 54%(150°C*0.5h) |
| Solvent | Alkylbenzene |
| Density | 0.93 – 0.95 g/cm ³ (20°C) |
| The refractive index | 1.464 – 1.474(25°C) |
| Flash point | 50°C |
| Appearance | Transparent to slight yellowish liquid(25°C) |

Addition and dosage

0.1 – 1.0% on total formulation. In general, under normal conditions, the dosage is 0.1 – 0.3% based on total formulation.

Incorporation

AFCONA-3031 can be incorporated at any stage of process.

Storage

AFCONA-3031 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 5 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

25kg and 180 kg non-returnable containers

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.