

AFCONA-3773



Chemical Composition

Fluorocarbon modified polyacrylate polymer.

Product general description

Anti-crater, substrate wetting and leveling agent for solvent-based coatings.

Product Properties

AFCONA-3773 is a fluorocarbon-modified polyacrylate. It is a silicone-free leveling agent, free from inter-coat adhesion problems. However, for enhanced overall performance, it is also recommended to combine it with a suitable silicone leveling agent for use in high-grade industrial topcoats.

AFCONA-3773 is a more cost-effective version compared to AFCONA-3777 and AFCONA-3777S. It offers moderate compatibility and strikes a good balance between leveling, post-flow control and defoaming properties, making it versatile and universal.

AFCONA-3773 has the following advantages:

- 1) Improves leveling of the coating.
- 2) Prevents cratering.
- 3) Helps substrate wetting.
- 4) Acts as a defoamer and deaerator.
- 5) Does not affect intercoat adhesion or recoatability.

AFCONA-3773 is recommended for:

- 1) All solvent-based baking systems for leveling and anti-crater agents.
- 2) Polyurethane systems for leveling, anti-crater and anti-foam agents.
- 3) Epoxy systems for leveling and anti-crater agents.

Product Specification

Non-volatile matter	69 - 71% (150°C,0.5h)
Solvent	Xylene
Density	0.96 - 0.99 g/cm ³ (20°C)
Gardner color	Max.3
Flash point	45°C
Appearance	Transparent to slightly yellowish liquid(25°C)

Addition and dosage

0.30-2.00% on total formulation. Under normal conditions, the dosage is 0.30-0.80% based on total formulation.

Incorporation

AFCONA-3773 should be incorporated at the end of the batch preparation.

Storage

AFCONA-3773 shall be stored in cool and dry place away from direct sunlight. Shelf-life is 5 years from the date of manufacturer, if kept in original and unopened container. The expiring date is indicated on the package.

Packaging

25kg and 200 kg non-returnable containers

For product safety information: please refer to the product SDS.

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.