

AFCONA – 4590



Chemical Composition

Modified polyacrylate polymer.

Product general description

High efficient polymeric dispersant for no grinding resin concentrate manufacturing. And it will give best color development of paint.

Product Properties

AFCONA-4590 is a high molecular weight wetting and dispersing agent, especially the stabilization to inorganic and carbon black. It has excellent stabilization to all types of pigments, behavior of its steric effect. The performance is close to AFCONA-4570, but much lower cost.

AFCONA-4590 has below advantages:

- Better Gloss;
- Good viscosity decrease;
- Prevent flocculation of pigments;
- Lighten floating problems;
- Improve the color development of pigments.

AFCONA-4590 is a modified polyacrylate highmolecular weight dispersant, it can be applied in water-based and solvent based coating systems, such as aqueous and solvent based decorative paints, aqueous and solvent based general industrial paints. It is best applied to aromatic free long oil alkyds with high solid content.

AFCONA-4590 also can improve the color acceptance of coating systems with aqueous and solvent based concentrates of markets, as well as general water/oil concentrates.

Note: AFCONA-4590 will become slightly hazy at temperatures below 5°C. This will not influence the quality.

Product Specification

| | |
|---------------------|--|
| Non-volatile matter | 40 - 43% (150°C,0.5h) |
| Solvent | Tripropylene Glycol Monomethyl Ether/Water |
| Density | 1.02 - 1.06 g/cm ³ (20°C) |
| Amine value | 34 - 50 mg KOH/g |
| Flash point | > 100°C |
| Gardner Color | Max.8 |
| Appearance | Transparent to slightly hazy, brownish liquid (25°C) |

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

| | |
|--------------------------|------------|
| TiO ₂ | : 2 - 3% |
| Other inorganic pigments | : 2 - 5% |
| Organic pigments | : 20 - 40% |
| Carbon blacks | : 20 - 60% |

Incorporation

AFCONA-4590 should be incorporated in the mill base before adding the pigments.

Storage

AFCONA-4590 should be stored in a cool dry place. When kept in an original unopened container, it will keep up to 3 years from the date of manufacture. The expiry date is indicated on the container.

Packaging

30kg and 200 kg non-returnable containers

For product safety information: please take reference of SDS.

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.