

AFCONA-5290



Chemical Composition

Polymer with pigment anchoring groups.

Product general description

100% solids high molecular weight dispersant.

Product Properties

AFCONA-5290 is a 100% solid dispersant created for high-solid systems and formulations that are facing VOC limitations.

The characteristics and recommended systems for AFCONA-5290 are as follows:

- 1) AFCONA-5290 is suitable for all solvent-based systems ranging from low to high polarity, including air-drying alkyd.
- 2) AFCONA-5290 has very good pigment stability and overall performance. It gives good viscosity reduction and high colour strength.
- 3) AFCONA-5290 is provided with almost 100% active ingredients; therefore, it is an excellent dispersant for high-solid coatings like polyurethane, epoxy and UV coating.
- 4) This product is a very interesting dispersant for ink formulations. The 100% active nature of AFCONA-5290 allows the formulator free choice of solvents for the finished product.

Note: AFCONA-5290 may become slightly hazy when stored at or below 5°C. This will not affect the quality and the dispersion performance.

Product Specification

Non-volatile matter	≥ 96% (120°C, 0.5h)
Density	1.00 - 1.04 g/cm ³ (20°C)
Acid value	7 - 15 mg KOH/g
Amine value	5 - 10 mg KOH/g
Flash point	>100°C
Appearance	Transparent to slightly hazy, brown liquid (25°C)

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

TiO ₂ and other fillers:	2.0 - 3.0%
Other inorganic pigments:	2.0 - 4.0%
Organic pigments:	20 - 40%
Carbon blacks:	20 - 60%

Incorporation

AFCONA-5290 should be added before pigment dispersion and mixed uniformly with the base resin system using shear force.

Storage

AFCONA-5290 shall be stored in cool and dry place away from direct sunlight. Shelf-life is 5 years from the date of manufacturer, if kept in original and unopened container. The expiring date is indicated on the package.

Packaging

25kg and 200kg non-returnable containers

For product safety information: please take reference of SDS.

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.