

AFCONA-K201-22



Chemical Composition

Solution of high molecular weight polymeric surfactant.

Product general description

High molecular weight wetting & dispersing agent for the preparation of carbon nanotubes and conductive carbon black concentrates.

Product properties

AFCONA-K201-22 is primarily used to enhance the wetting & dispersing performance in carbon nanotubes and conductive carbon black concentrates by improving grinding efficiency and reducing the viscosity.

AFCONA-K201-22 can also reduce the viscosity of cathode slurry in lithium-ion battery systems, optimizing flow-ability and flocculation state, and increase powder loading capacity.

Note: AFCONA-K201-22 contains specially-structured functional materials that may develop slight sedimentation during prolonged storage. Overall performance won't be affected if adequate additional shear is applied before its use.

Product Specification

Non-volatile matter	52 - 56% (150°C, 0.5h)
Solvent	N-Methylpyrrolidone
Density	1.11 - 1.15 g/cm ³ (20°C)
Acid value	18 - 28 mg KOH/g
Amine value	25 - 35 mg KOH/g
Flash point	86°C
Appearance	Black viscous liquid (25°C)

Addition and dosage

Calculation method for the required amount of active ingredient on pigment:

Carbon nanotubes : 20 - 40%
Conductive carbon blacks : 30 - 50%

Incorporation

AFCONA-201-22 should be stirred and uniformly dispersed with NMP, then the powder material should be added slowly under shear force.

Storage

AFCONA-K201-22 shall be stored in a cool dry place at temperature above 4°C. Shelf-life is 6 months from the date of manufacturer, if kept in original and unopened container. The expiring date is indicated on the package.

Packaging

30kg and 220kg non-returnable containers

For product safety information: please take reference of SDS.

AFCONA ADDITIVES

Web Site : www.afcona.com

This information and all further technical advice are based on our present knowledge and experience. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used. We reserve the right to make any changes according to science and technological progress or further developments.

This version replaces all previous ones.